

STURDI - SPAN



www.whirlwindsteel.com



WHIRLWIND STEEL BUILDINGS, INC.

Building Systems | Building Components | Solar Energy Systems
 Corporate Headquarters • 8234 Hansen Rd, Houston, TX 77075
 (Phone) 713.946.7140 | (Fax) 832.553.4700 | (US Wats) 800.324.9992

STURDI-SPAN / STURDI-SPAN X



STURDI-SPAN DESIGN PROPERTIES						
PANEL GAUGE	F _y (KSI)	WEIGHT (PSF)	TOP IN COMPRESSION		BOTTOM IN COMPRESSION	
			I _x (In ⁴ -Ft)	M _x (In-Kip)	I _x (In ⁴ -Ft)	M _x (In-Kip)
29	80*	0.65	0.0070	0.5023	0.0050	0.5247
26	80*	0.80	0.0090	0.6517	0.0060	0.6437
26	50	0.80	0.0093	0.5677	0.0067	0.5517

* F_y is 80-ksi reduced to 60-ksi in accordance with the 2007 edition of the North American Specification For Design Of Cold-Formed Steel Structural Members - A2.3.2.

NOTES:

- All section properties are calculated in accordance with the 2007 edition of the North American Specification For Design Of Cold-Formed Steel Structural Members.
- I_x is for deflection determination.
- M_x is allowable bending moment.

MATERIALS

Unless otherwise specified, the exposed surfaces of all panels shall be either clear acrylic coated GALVALUME®, Chem-Treated G90 galvanized, factory painted G60 galvanized or factory painted AZ50 Galvalume®. GALVALUME® is a 55% aluminum-zinc alloy-coated steel material. Acrylic coated GALVALUME® shall have a Coating Class AZ55. Galvanized is a zinc-coated steel material. Chem-treated galvanized shall have a Coating Designation G90. Factory painted galvanized shall have a Coating Designation G60 or G90. Panels shall conform to ASTM A653, Structural Steel.

PAINTED FINISH

All painted panels shall be factory coated by a firm which coats coil products exclusively. The coater shall be responsible for ensuring color consistency, paint film hardness, and paint film thickness. Each side of the panels will be coated with 0.2 mils baked-on primer before the color coating. The 29 and 26 gauge panels shall receive a baked-on silicone polyester finish coat on the exposed side. Thickness of the finish coat will be a nominal 1.0 mils (including the primer coat). A baked-on straight polyester wash coat will be applied on the non-exposed side. Thickness of the wash coat will be a nominal 0.5 mils (including the primer coat).

LIMITED MATERIAL WARRANTY

Specific conditions concerning each finish shall be covered in detail on the written warranty issued, on request, with each order. Minimum roof slope - 3:12 (where snow load controls). GALVALUME® panels shall have a twenty-five year limited warranty providing that GALVALUME® panels will not rupture, fail structurally, or perforate within a period of twenty-five years after shipment due to exposure to normal atmospheric corrosion. The clear acrylic finish does not carry a warranty. The 29 and 26 gauge factory painted Galvanized panel shall have a thirty-year limited color finish warranty from peeling and cracking, and a twenty-five year limited color finish warranty from excessive chalking and color change (fading). The wash coat does not carry a warranty.

ROOF PANELS

Panel coverage will be 36" to the weather. Maximum panel length shall be 40'-0". Where endlaps are required, they shall be a minimum of 6" and shall occur at a purlin or girt. Panels shall be furnished square cut. Wall panels must not rest on the concrete foundation; the panel must sit 1/8" above the concrete. All installations shall be in accordance with standard industry practices. Before securing, all laps of roof panels shall be sealed with a continuous ribbon of tape sealant. A closure strip shall be installed at the eave. Panels shall be secured to intermediate framing members with sheet metal screws at a maximum spacing of 9" on center. At endlaps, the maximum screw spacing shall be 6" on center (one on each side of the major rib).

- **UL 580 UP-LIFT TESTED CLASS 90 RATED (29GA MIN.)**
- **UL 2218 HAIL IMPACT RESISTANT TESTED INCLINED: UNLIMITED IMPACT: CLASS 4**
- **FLORIDA PRODUCT APPROVAL FL# 11471**

Houston, TX
(800) 324-9992

Lithia Springs, GA
(800) 363-8142

Claremore, OK
(877) 875-0077

Freeport, MN
(888) 836-7203